

2001

BOLTARON

2001 TruPrint

GENERAL INFORMATION

TruPrint 2001 is a homopolymer print stock of high quality rigid vinyl, suitable for virtually all printing applications.

TruPrint 2001 offers flexibility of print surfaces to fit your specific needs. This product is designed to meet all the PVC fabricators requirements expected in printing, embossing, die cutting, folding, and laminating.

TruPrint 2001 alloy can be used in single core or laminated core applications and is compatible with coated or uncoated overlays.

TruPrint 2001 print stock offers excellent performance characteristics, making it the ideal product for most applications.

AVAILABILITY

Gauges- (.006" - .030")
Colors- Custom
Sizes- Custom

SUGGESTED APPLICATIONS

Die Cut Templates
P.O.P. Displays
Labels
I.D.Tags
Promotional Cards
Phone Cards
Card Blanks
Fare Cards
File Folders

Typical Physical Properties

Property	Test Method	Typical values
Specific gravity	ASTM D-792	1.42 - 1.45
Tensile strength (PSI)	ASTM D-638	5,500
Tensile modulus (PSI)	ASTM D-638	3.9×10^5
Flexural strength (PSI)	ASTM D-790	8,700
Flexural modulus (PSI)	ASTM D-790	3.8×10^5 - 4.2×10^5
Izod impact (Ft. lbs./in. of notch)	ASTM D-256	1.5-5
Hardness Rockwell R	ASTM D-785	106
Heat Deflection (°F) 264 PSI (annealed)	ASTM D-648	160
Vicat Softening point (°C)	ASTM D-1525	80 ±2

LIMITATION OF WARRANTY

The application suggestions, specifications and other data described here are based upon experience and information that is believed, by BPP to be reliable. However, BPP makes no express or implied warranty that BOLTARON 2001 will perform in accordance with such specifications in any particular circumstance. Therefore, ALL EXPRESS OR IMPLIED WARRANTIES IN CONNECTION WITH BOLTARON 2001, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY DISCLAIMED. The prospective user should determine the suitability of BOLTARON 2001 and the application suggestions before actual application.

One General Street, Newcomerstown, OH 43832
P 800.342.7444 F 740.498.5448 E info@boltaron.com
www.boltaron.com