

Boltaron® 4050

TYPE II PVC

CHARACTERISTICS

- High impact
- Corrosion resistant
- Suitable for thermoforming
- Conforms to ASTM D1784
- Smooth finish
- Meets LP535A Comp A

USES

- Linings and thermoformed parts
- Machined parts
- Fume hoods
- Acid etching, and acid tanks

PERFORMANCE DETAILS

PROPERTIES

Specific Gravity (ASTM D792)	1.35	
Tensile Strength (ASTM D638)	5,600 psi	39 MPa
Elongation Ultimate (ASTM D638)	122%	
Elongation Yield (ASTM D638)	4%	
Modulus of Elasticity (ASTM D638)	3.2 x10 ⁵ psi	2,206 MPa
Flexural Strength (ASTM D790)	8,000 psi	55 MPa
Flexural Modulus (ASTM D790)	3.0 x10 ⁵ psi	2,068 MPa
Izod Impact Notched (ASTM D256)	73 °F 10-15ft-lb/in	23 °C 534-801J/m
Hardness Rockwell R (ASTM D785)	116	
Hardness Shore D (ASTM D2240)	80	
Compression Strength (ASTM D695)	8,000 psi	55 MPa
Shear Strength (ASTM D732)	6,500 psi	45 MPa
Water Absorption (24 hrs.)	0.056 %	

*Independent lab tests at 73°F (22.8°C) in dry conditions unless otherwise noted.

SHEET SIZES

Lengths	to 96 in	2,438 mm
Widths	to 48 in	1,219 mm
Gauges	from 0.032 to 2 in	from 0.813 to 50.8 mm

Custom Blank sizes, gauges on request

THERMAL PROPERTIES

Thermal Expansion (ASTM D696)	1.80x10 ⁻⁰⁵ °F	3.20 x10 ⁻⁰⁵ °C
Heat Deflection Annealed (ASTM D648)	160°F @264 psi	71°C @1.8 MPa
Thermal Conductivity (ASTM C177)	0.74 BTU/HR/FT/F	
Specific Heat (ASTM C351)	0.21 CAL/GM/°C	

ELECTRICAL PROPERTIES

Dielectric Strength (ASTM D149)	335 Volts/Mil.
Dielectric Constant (ASTM D150)	2.85 @60Hz
Dissipation Factor (ASTM D150)	0.016 @60Hz
Loss Index (ASTM D150)	0.045 @60Hz
Volume Resistivity (ASTM C257)	1.8 x 10 ¹⁴ Ohms/cm

FLAMMABILITY

UL 94	V-0
--------------	-----

*Values based on minimum thickness of .030 inches (.75 mm), UL File #E54688.

CORROSION
RESISTANT

4050
TYPE II PVC

DESIGN OPTIONS

- Colors** Medium Gray (2103)
- Textures** Smooth polished surface (both sides)
- Masking** Upon request

SIMONA
boltaron

www.boltaron.com | +1 800 342 7444

RELIABILITY MEETS INNOVATION

DISCLAIMER AND LIMITATION OF WARRANTY: All information contained herein is believed by SIMONA BOLTARON Inc. to be reliable. Typical properties are based on laboratory tests conducted on material samples in accordance with standard test methodology. SIMONA BOLTARON Inc. makes no express or implied warranty that its products will perform in accordance with the data in all conditions and circumstances. To determine suitability for use, users must test applications under actual operating conditions. As a result, ALL EXPRESS OR IMPLIED WARRANTIES IN CONNECTION WITH SIMONA BOLTARON Inc. PRODUCTS INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. RI 10.14.23